



# LS-61 A/B BRUSHABLE 60 SHORE A POLYURETHANE ELASTOMER

## PRODUCT HIGHLIGHTS:

LS-61 is a multi-purpose elastomer that can perform many functions. Special product characteristics are:

- Smooth thixotropic consistency makes application by brush or trowel easy
- Resists moisture absorption
- Convenient 1 to 1 mix ratio by weight
- Abrasion and impact resistant
- Cures fully at ambient temperatures in thicknesses ranging from 1/16" to 1/2"

## PHYSICAL PROPERTIES:

Hardness, Shore A ASTM D-2240.....	60 ± 5
Density, (g/cc) ASTM D-792.....	0.92
Cubic Inches per pound.....	29.8
Color/Appearance.....	Opaque cream
Tensile Strength, (psi) ASTM D-412.....	850
Tensile Modulus, (psi) ASTM D-412.....	420
Elongation, (%) ASTM D-412.....	435
Tear Strength, (pli) ASTM D-624 .....	140

## HANDLING PROPERTIES:

Mix Ratio (by weight):

Part A .....	100 parts by weight
Part B .....	100 parts by weight

Mix Ratio (by volume):

Part A .....	73 parts by volume
Part B .....	100 parts by volume

Specific Gravity:

Part A .....	1.08
Part B .....	0.78

Color:

Part A .....	yellow/clear
Part B .....	opaque cream

Viscosity, (cps) @ 77°F (25°C):

Part A .....	13,500
Part B .....	88,000
Mixed.....	Semi-paste

Work Time, (100g mass) @ 77°F (25°C)..... 20-30 minutes

Gel Time .....

35 minutes

Demold Time @ 77°F (25°C)..... 4 - 5 hours

**CURE SCHEDULE/HEAT CURING:**

Most of the physical properties can be achieved in 5-7 days at ambient temperature, 77°F (25°C). In order to achieve maximum physical properties, a post cure with heat is required. BJB recommends 24 hours at ambient temperature, 77°F (25°C), followed by 16 hours at 160°F (71°C).

**MOLD PREPARATION AND RELEASING:**

When LS-61 A/B is used to reproduce molds from plaster, wood or other porous substrates, we would first recommend that they be sealed. Release agents may then be applied over the sealed surface. Consult with BJB’s technical staff for specific release agent recommendations.

**NOTE:**

Prolonged direct exposure to sunlight can affect the surface of this product. Cover molds or other products when storing outdoors. **The cure will be inhibited if cast against a tin catalyzed silicone RTV.**

**STORAGE:**

Store at room temperature in a dry place. Opened containers of material should be purged with dry nitrogen or an equivalent product, prior to replacing lids or caps to prevent moisture contamination. Shelf life is 6 months from date of shipment in unopened containers.

**PACKAGING:**

1 Gallon kits..... 5 lbs. A, 5 lbs. B  
5 Gallon kits..... 25 lbs. A, 25 lbs. B

**SAFETY PRECAUTIONS:**

Use in a well-ventilated area. Avoid contact with skin using protective gloves and protective clothing. Repeated or prolonged contact on the skin may cause an allergic reaction. Eye protection is extremely important. Always use approved safety glasses or goggles when handling this product.

**IF CONTACT OCCURS:**

**Skin:** Immediately wash with soap and water. Remove contaminated clothing and launder before reuse. It is *not* recommended to remove resin from skin with solvents. Solvents only increase contact and dry skin. Seek qualified medical attention if allergic reactions occur.

**Eyes:** Immediately flush with water for at least 15 minutes. Call a physician.

**Ingestion:** If swallowed, call a physician immediately. Remove stomach contents by gastric suction or induce vomiting only as directed by medical personnel. Never give anything by mouth to an unconscious person.

**Refer to the Material Safety Data Sheet before using this product.**

NON-WARRANTY "Except for a warranty that materials substantially comply with the data presented in Manufacturer's latest bulletin describing the product (the basis for this substantial compliance is to be determined by the standard quality control tests generally performed by Manufacturer), all materials are sold "AS IS" and without any warranty express or implied as to merchantability, fitness for a particular purpose, patent, trademark or copyright infringement, or as to any other matter. In no event shall Manufacturer's liability for damages exceed Manufacturer's sale price of the particular quantity with respect to which damages are claimed."