



# WC-775 A/B

## WATER CLEAR 75 SHORE D

### POLYURETHANE CASTING SYSTEM

#### PRODUCT DESCRIPTION:

WC-775 A/B produces a high impact rigid 75 Shore D material that is commonly used to make clear or tinted castings of all kinds. When used at room temperature, castings  $\frac{1}{8}$ " thick or larger can be readily cast. Castings that are less than  $\frac{1}{8}$ " thick will generally require a mild post-cure. This product may exhibit a slight yellowing or color change when exposed to direct UV light.

#### PRODUCT HIGHLIGHTS:

- Exceptional clarity
- High impact resistance
- 15 minute working time
- Good weather ability

#### PHYSICAL PROPERTIES:

Hardness, Shore D ASTM D-2240.....	75 ± 2
Density, (g/cc) ASTM D-792.....	1.09
Cubic Inches Per Pound.....	26.6
Color/Appearance.....	Water clear/colorless
Tensile Strength, (psi) ASTM D-638.....	6,900
Tensile Modulus, (psi) ASTM D-638.....	$2.7 \times 10^5$
Elongation, (%) ASTM D-638.....	62
Flexural Strength, (psi) ASTM D-790.....	7,900
Flexural Modulus, (psi) ASTM D-790.....	$2.1 \times 10^5$
Shrinkage, (in./in.) linear 12" x ½" x ½".....	0.005
Izod Impact, notched (ft.-lb./in.) ASTM D-256.....	1.16

#### HANDLING PROPERTIES:

##### Mix Ratio (by weight):

Part A.....	95 parts by weight
Part B.....	100 parts by weight

##### Mix Ratio (by volume):

Part A.....	92 parts by volume
Part B.....	100 parts by volume

##### Specific Gravity:

Part A.....	1.06
Part B.....	1.03

##### Viscosity, (cps) @ 77°F (25°C) Brookfield:

Part A.....	600 ± 50
Part B.....	400
Mixed.....	650 ± 50

**HANDLING PROPERTIES (continued):**

Color:

Part A .....	Clear/colorless
Part B .....	Clear/colorless
Work Time, (100-gram mass) @ 77°F (25°C).....	15 minutes
Demold Time @ 77°F (25°C).....	16 - 24 hours

**CURE SCHEDULE/HEAT CURING:**

Most of the physical properties can be achieved in 5-7 days at ambient temperature, 77°F (25°C). In order to achieve maximum physical properties, a post cure with heat is required. BJB recommends 24 hours at ambient temperature, 77°F (25°C), followed by 16 hours at 180°F (82°C). Support of the part may be required to prevent part deformation during heat cure.

**NOTE:**

**The cure will be inhibited if cast against a tin catalyzed silicone RTV.**

**STORAGE:**

Store in a cool dry place. Unopened containers will have a shelf life of 6 months from date of shipment when properly stored at room temperatures. Purge opened containers with dry nitrogen before re-sealing.

**PACKAGING:**

Gallon Kits.....	7.6 lbs. A, 8 lbs. B
5 Gallon Kits.....	38 lbs. A, 40 lbs. B
55 Gallon Drum Kits.....	380 lbs. A, 400 lbs. B

**SAFETY PRECAUTIONS:**

Avoid contact with skin using protective gloves and protective clothing. Repeated or prolonged contact on the skin may cause an allergic reaction. Eye protection is extremely important. Always use approved safety glasses or goggles when handling this product. Use in well-ventilated areas. Avoid breathing vapors. If exposures cannot be kept at a minimum, a respirator may be necessary in addition to ventilation. The use of a positive pressure air supplied respirator is mandatory when airborne isocyanate concentrations are "not known" or exceeds OSHA'S TWA of 0.005 ppm. Air purifying, organic cartridge type respirators are not generally recommended to use when handling this material without implementation of an end of life service program. Observe OSHA regulations for respirator use (29 CFR 1910.134). Employers are responsible for selecting the correct respirator for each situation.

**IF CONTACT OCCURS:**

- Skin:** Immediately wash with soap and water. Remove contaminated clothing and launder before reuse. It is *not* recommended to remove resin from skin with solvents. Solvents only increase contact and dry skin. Seek qualified medical attention if allergic reactions occur.
- Eyes:** Immediately flush with water for at least 15 minutes. Call a physician.
- Ingestion:** If swallowed, call a physician immediately. Remove stomach contents by gastric suction or induce vomiting only as directed by medical personnel. Never give anything by mouth to an unconscious person.

**Refer to the Material Safety Data Sheet before using this product.**

NON-WARRANTY "Except for a warranty that materials substantially comply with the data presented in Manufacturer's latest bulletin describing the product (the basis for this substantial compliance is to be determined by the standard quality control tests generally performed by Manufacturer), all materials are sold "AS IS" and without any warranty express or implied as to merchantability, fitness for a particular purpose, patent, trademark or copyright infringement, or as to any other matter. In no event shall Manufacturer's liability for damages exceed Manufacturer's sale price of the particular quantity with respect to which damages are claimed."